

# HIGH TECH GREASES



PRODUCT	CHEMICAL BASIS	NLGI Grade	Color	Carrier	Weld Load	AW Scar	Water wash out	EMCOR TEST	Water	Water	HEAVY DUTY APPLICATIONS			MEDIUM AND LOW DUTY APPLICATIONS			
					Kg	Diameter mm	at 38°C % Loss	Distilled Water	Spray Off % Loss	Spray Off + Tackifier % Loss	Steel Mills Paper Mills	Marine Off shore	Heavy industry	Food Industries	Agriculture	Automotive Trucks	Construction
					ASTM D 2596	ASTM D 2266	ASTM D 1264	ISO 11007	ASTM D4049	ASTM D4049							
ARCOT 645	Overbased calcium sulfonate carbonate	0	Beige Brown	Mineral Oil ISO 68	400	0,6	7	0 / 0	99	70	♦	♦	♦		♦	♦	♦
ARCOT 645 H	Overbased calcium sulfonate carbonate	1	Beige Brown	Mineral Oil ISO 460	400	0,5	6	0 / 1	68	20	♦	♦	♦		♦	♦	♦
ARCOT 645 G	Overbased calcium sulfonate carbonate	2	Beige Brown	Mineral Oil ISO 460	500	0,5	1	0 / 1	31	10	♦	♦	♦		♦	♦	♦
ARCOT 645 U	Overbased calcium sulfonate carbonate	3	Beige Brown	Mineral Oil ISO 460	500	0,5	6	2 / 2	11	5	♦	♦	♦		♦	♦	♦
<b>BIODEGRADABLE GRADE</b>																	
KELICO BG	Overbased calcium sulfonate carbonate	2	White	Ester iso 46	400	0,8	3	2 / 2	98		♦	♦	♦		♦	♦	♦
<b>FOOD GRADE H1 and H1X</b>																	
KELICO FG	Overbased calcium sulfonate carbonate	2	White	White oil ISO 100	500	0,6	6	2 / 2	96	29	♦	♦	♦	♦	♦	♦	♦

